

CHEMISTRY. CHEMICAL ENGINEERING

ХІМІЯ. ХІМТЕХНОЛОГІЯ

UDC 661.682

I. Kayun,

O. Musov, PhD, Assoc.Prof.,

Ukrainian State University of Chemical Technology, 8 Gagarin Ave., Dnipropetrovsk, Ukraine, 49005; e-mail: igorkayun@ukr.net

THERMODYNAMIC OF OBTAINING OF MONODISPERSE PARTICLES SiO_2 BY TETRAETHOXYSILANE HYDROLYSIS IN THE SI-O-H-C-N SYSTEM

І.Г. Каюн, О.П. Мусов. Термодинаміка отримання монодисперсних частинок SiO_2 гідролізом тетраетоксисилану в системі Si-O-H-C-N. Висвітлено проблему синтезу монодисперсних частинок SiO_2 гідролізом $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$ за методом Штобера. Метою дослідження є визначення умов проходження даної реакції у водно-аміачно-спиртовому середовищі при яких досягається максимальна концентрація твердої фази SiO_2 та мінімальна концентрація іонних сполук силіцію в розчині. Шляхом термодинамічного моделювання досліджений склад системи Si-O-H-C-N при термодинамічній рівновазі для різних заданих умов. Отримання максимальної кількості твердої фази SiO_2 при різних початкових концентраціях $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$ досягається при початковій концентрації $\text{C}_2\text{H}_5\text{OH}$ більше 1,2 моль/л, концентрація твердої фази SiO_2 пропорційна початковій концентрації $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$. Термодинамічні дослідження показують, що зміна температури реакції від 1 до 70 °C не впливає на концентрації іонних сполук силіцію в розчині та твердої фази SiO_2 . Отримані результати зменшують область пошуку оптимальних умов отримання монодисперсних частинок SiO_2 та дають можливість більш глибоко зрозуміти процеси що протікають в системі Si-O-H-C-N.

Ключові слова: термодинаміка, метод Штобера, гідроліз тетраетоксисилану

I. Kayun, O. Musov. Thermodynamic of obtaining of monodisperse particles SiO_2 by tetraethoxysilane hydrolysis in the Si-O-H-C-N system. The problem of synthesizing of mono disperse SiO_2 particles with hydrolysis $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$ by the Stober method is described. The purpose of the study is to determine the conditions for the passage of this reaction in a water-ammonia-alcohol medium, at which the maximum concentration of the solid phase of SiO_2 and the minimum concentration of silicon ion compounds in solution are reached. By thermodynamic modeling the composition of the Si-O-H-C-N system under thermodynamic equilibrium for various given conditions was studied. The maximum amount of solid phase SiO_2 at different initial concentrations $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$ is achieved at an initial concentration of $\text{C}_2\text{H}_5\text{OH}$ more than 1.2 mol/l, the concentration of the solid phase of SiO_2 is proportional to the initial concentration $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$. Thermodynamic studies show that a change in the reaction temperature from 1 to 70 °C does not affect the concentration of ionic silicon compounds in the solution and the solid phase of SiO_2 . The obtained results reduce the search for optimal conditions for the production of monodisperse particles of SiO_2 and allow a deeper understanding of the processes taking place in the Si-O-H-C-N system.

Keywords: thermodynamics, Stober method, hydrolysis of tetraethoxysilane

Introduction. Actuality obtaining of mono-dispersed particles of SiO_2 due to their wide use in industry. This is the production of opals, photonic crystals, in the chemical industry as composite catalysts, etc.

Hydrolysis of tetraethoxysilane (TEOS) by the Stoeber method in a water-alcohol-ammonia medium allows for the obtaining of nano and submicron spherical particles of SiO_2 [1]. The size of SiO_2 particles synthesized by hydrolysis of TEOS largely depends on the concentration of TEOS, water, alcohol, ammonia and reaction temperature [2].

Due to the many components of the Si-O-H-C-N system, the development of technology for the synthesis of mono disperses spherical particles of SiO_2 requires numerous experiments. Thermodynamic studies will reduce their number, determine the conditions for which the maximum solid phase of SiO_2 will be obtained and determine the composition of the Si-O-H-C-N system, which greatly affects the characteristics of the synthesized particles [3].

Analysis of recent research and publications. The influence of water, ammonia and TEOS concentrations on the particle diameter and their uniformity in size was considered repeatedly [4]. The possibility to obtain homogeneous particle sizes at high concentrations of TEOS [5] was investigated.

DOI: 10.15276/opu.1.54.2018.10


© 2018 The Authors. This is an open access article under the CC BY license (<http://creativecommons.org/licenses/by/4.0/>).

The described work only partially investigated the problem of synthesis of monodisperse particles SiO_2 . Restrict the search area of optimal conditions for the production of mono-dispersed SiO_2 particles is possible by thermodynamic studies. The thermodynamic study of tetraethoxysilane hydrolysis by the stoeber method has been given insufficient attention. There are studies that only partially describe the properties of the multi-component system Si-O-H-C-N. Calculated and experimentally confirmed data of thermo chemical parameters for 47 molecules in the Si-O-H system [6]. The thermo chemistry of compounds that can exist in the early stages of the high-temperature decomposition of TEOS in the preparation of amorphous silicon dioxide ($\alpha\text{-SiO}_2$) nano particles [7] is investigated.

Thus, the Si-O-H-C-N system, represented by tetraethoxysilane in a water-alcohol-ammonia environment, is not investigated from thermodynamic positions. However, there is information on the thermodynamic parameters of the compounds that make up the investigated system and can be formed as a result of the reaction.

The purpose of the study is to determine the conditions for the hydrophilic reaction of the TEOS in aqueous ammonia-alcoholic medium, in which the maximum concentration of SiO_2 solid phase and the minimum concentration of ionic compounds of silicon in the solution is reached.

Presentation of the main material. Synthesis of monodisperse particles of SiO_2 by hydrolysis of TEOS by the Stoeber method is carried out by reaction (1) in a water-alcohol-ammonia environment.



The reaction components (1) form a system of Si-O-H-C-N, the thermodynamic studies of which are well described by a mathematical model created on the basis of the "Selector" software complex. The principle embodied in the program is based on minimizing the isobaric-isothermal potential of Gibbs.

In thermodynamic calculations, the following assumptions were adopted: the *Si-O-H-C-N* system is at constant temperature and atmospheric pressure. In the thermodynamic model, the standard "Selector" databases are used: Yokokawa, sprons98, sprons07, dump. The model includes the following components:

Solid phase: NH_4NO_3 , SiC, Si, SiO_2 ;

Gas phase: NH_3 , C_2H_4 , CO_2 , CO, H_2 , CH_4 , N_2 , $\text{C}_7\text{H}_8\text{O}$, O_2 , $\text{C}_6\text{H}_6\text{O}$, H_2O ;

Aqua solution: H_4SiO_4 , $\text{H}_2\text{SiO}_4^{-2}$, H_3SiO_3^+ , H_3SiO_4^- , $\text{CH}_3\text{CONH}_2^*$, $\text{C}_2\text{H}_3\text{O}_2^-$, $\text{C}_2\text{H}_4\text{O}_2^*$, $\text{C}_4\text{H}_7\text{O}_2^-$, CO^* , CO_2^* , CO_3^{-2} , C_2H_6^* , $\text{C}_2\text{H}_5\text{OH}^*$, HCO_2^- , H_2CO_2^* , $\text{C}_2\text{H}_5\text{NO}_2^*$, $\text{C}_3\text{H}_3\text{O}_4^-$, C_2HO_4^- , H_2^* , HCO_3^- , HSiO_3^- , $\text{C}_3\text{H}_2\text{O}_4^{-2}$, CH_3NH_2^* , CH_3OH^* , N_2^* , NH_3^* , $\text{NH}_4\text{CH}_3\text{COO}^*$, $\text{NH}_4(\text{CH}_3\text{COO})_2^-$, NH_4^+ , OCN^- , $\text{C}_2\text{O}_4^{-2}$, C_3H_8^* , $\text{C}_3\text{H}_5\text{O}_2^-$, $\text{C}_3\text{H}_6\text{O}_2^*$, SiO_2^* , $\text{H}_2\text{NCONH}_2^*$, OH^- , H^+ , H_2O .

The described thermodynamic model shows that the amount of solid phase SiO_2 depends on the concentration of $\text{C}_2\text{H}_5\text{ON}$. At the initial concentrations of $\text{H}_2\text{O}=20$ M, $(\text{C}_2\text{H}_5\text{O})_4\text{Si}=0.1$ M, $\text{NH}_4\text{OH}=1.5$ M and at a temperature $T=25$ °C, the maximum solid phase of SiO_2 is formed at a concentration of $\text{C}_2\text{H}_5\text{ON}$ greater than 0.9 M (Fig. 1). When the amount of alcohol from 0 M to 0.9 M changes, the concentration of $\text{H}_2\text{SiO}_4^{-2}$, H_3SiO_4^- , HSiO_3^- decreases with exponential dependence. A further increase in $\text{C}_2\text{H}_5\text{OH}$ has little effect on their number. The concentrations of other compounds of silicon C are lower than those described above, so it is possible to assume that they will not affect the characteristics of the synthesized particles.

In order to obtain the maximum SiO_2 solid phase at different initial $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$ concentrations, we established the required concentration of $\text{C}_2\text{H}_5\text{OH}$ (Fig. 2), which can be determined by equation (2). Thus under conditions of thermodynamic equilibrium for any initial concentrations $(\text{C}_2\text{H}_5\text{O})_4\text{Si}$ the maximum amount of SiO_2 solid phase is reached at an initial concentration of $\text{C}_2\text{H}_5\text{OH}$ of more than 1.2 mol/l.

$$y = 1,2 - 4 * [\text{Si}(\text{C}_2\text{H}_5\text{O})_4] . \quad (2)$$

In order to increase the SiO_2 solid phase, it is expedient to increase the initial number of TEOS. Fig. 3 shows the simulation results of the system Si-O-H-C-N at a temperature $T=25$ °C, which consisted of $\text{H}_2\text{O}=20$ M, $\text{C}_2\text{H}_5\text{OH}=9$ M, $\text{NH}_4\text{OH}=1.5$ M. As can be seen from Fig. 3 concentrations of SiO_2 and TEOS are proportional.

Concentrations of other compounds of silicon are practically unchanged. Simulation is limited by the maximum number of TEOS at which it is possible to obtain uniform spherical particles of size [3].

An increase in the initial concentration of NH_4OH from 0 to 1.9 M leads to a decrease in the SiO_2 solid phase in the Si-O-H-C-N system at 1e^{-5} M at a TEOS concentration of 0.2 M (Fig. 4). Subsequent studies have shown that the indicated change in the solid phase SiO_2 concentration does not depend on the concentration of TEOS.




Fig. 1. Dependence of the concentration of silicon compounds ($\blacklozenge$ - H_4SiO_4 , $\blacksquare$ - $\text{H}_2\text{SiO}_4^{2-}$, $\blacktriangle$ - H_3SiO_4^- , $\bullet$ - HSiO_3^- , $+$ - SiO_2^* , $\circ$ - SiO_2) from the initial concentration of $\text{C}_2\text{H}_5\text{OH}$ at the thermodynamic equilibrium of the Si-O-H-C-N system




Fig. 2. The concentration of alcohol is required to obtain the maximum amount of SiO_2 solid phase at different initial concentrations $\text{Si}(\text{C}_2\text{H}_5\text{O})_4$




Fig. 3. The dependence of the concentration of silicon compounds ($\blacklozenge$ - H_4SiO_4 , $\blacksquare$ - H_3SiO_3^+ , $\blacktriangle$ - H_3SiO_4^- , $\bullet$ - HSiO_3^- , $+$ - SiO_2^* , $\circ$ - SiO_2) from the initial concentration of TEOS at the thermodynamic equilibrium of the Si-O-H-C-N system




Fig. 4. The dependence of the concentration of silicon compounds ($\blacklozenge$ - H_4SiO_4 , $\blacksquare$ - H_3SiO_3^+ , $\blacktriangle$ - H_3SiO_4^- , $\bullet$ - HSiO_3^- , $+$ - SiO_2^* , $\circ$ - SiO_2) from the initial concentration of NH_4OH at the thermodynamic equilibrium of the Si-O-H-C-N system

It is known that for the complete passage of reaction (1), the minimum concentration of H_2O should be twice as high as the concentration of $\text{Si}(\text{OC}_2\text{H}_5)_4$. Given the experimental data, the indicated ratio should be greater [8].

Thermodynamic studies of the influence of the initial concentration of H_2O are shown in Fig. 5 (initial modeling conditions: $\text{NH}_4\text{OH}=1$ M, $\text{C}_2\text{H}_5\text{OH}=9$ M, $(\text{C}_2\text{H}_5\text{O})_4\text{Si}=0.2$ M, $T=25$ °C) show that SiO_2 can be obtained at an initial concentration of H_2O equal to 0 M.

Since the model shows the thermodynamic equilibrium of the system Si-O-H-C-N, which is not limited in time, H_2O in the system is formed with NH_4OH and $\text{C}_2\text{H}_5\text{ON}$ and it is sufficient for the complete passage of the reaction (1). Taking into account the kinetic constraints on obtaining SiO_2 particles, it is expedient to provide an initial ratio of $\text{H}_2\text{O}/\text{Si}(\text{OC}_2\text{H}_5)_4 > 2$ concentrations.

Investigated temperature range is due to boiling of the reaction mixture and its freezing is from 1 to 70 °C. Table 1 shows the simulation results of the system Si-O-H-C-N consisting of $\text{H}_2\text{O}=20$ M,

$C_2H_5OH = 9 \text{ M}$, $(C_2H_5O)_4Si = 0.2 \text{ M}$, $NH_4OH = 1.5 \text{ M}$. Thus, under thermodynamic equilibrium conditions, the temperature change of the system is not affects the concentration of compounds of silicon in the solution and solid SiO_2 phase.

Table 1

Concentrations of compounds at the thermodynamic equilibrium of the Si-O-H-C-N system in the temperature range from 1 to 70 °C

Compound	H_4SiO_4	$H_2SiO_4^{-2}$	$H_3SiO_3^{+}$	$H_3SiO_4^{-}$	$HSiO_3^{-}$	SiO_2^{*}	SiO_2
Concentration, mol/l	2.85E-05	1.28E-13	3.24E-10	8.80E-09	1.35E-08	9.52E-06	2.00E-01

The results of the thermodynamic calculations show that SiO_2 solids in the Si-O-H-C-N system are formed at a wide variation of the reaction temperature and the concentrations of reagents (Table 2).

Table 2

The ranges of variations of the parameters of the system S-O-H-C-N, in which a solid SiO_2 phase is formed

Parameter	Concentration $Si(OC_2H_5)_4$	Concentration H_2O	Concentration NH_4OH	Concentration C_2H_5OH	Temperature
Value range	0...1.2 M	0...19 M	0...1.9 M	0...10 M	1...70 °C

The experimental verification of theoretical studies was carried out at a temperature of $T=25 \text{ °C}$ and the concentrations of reagents $H_2O=20 \text{ M}$, $C_2H_5OH=10 \text{ M}$, $(C_2H_5O)_4Si=0.2 \text{ M}$. Experimental studies show that the practical yield of SiO_2 is less than the theoretical by 10...15 %, depending on the initial concentration of NH_4OH (Fig. 6).




Fig. 5. Dependence of the concentration of silicon compounds ($\blacklozenge$ - H_4SiO_4 , $\blacksquare$ - $H_3SiO_4^{-}$, $\bullet$ - $HSiO_3^{-}$, $+$ - SiO_2^{*} , $\circ$ - SiO_2) from the initial concentration of H_2O at the thermodynamic equilibrium of the Si-O-H-C-N system




Fig 6. Comparison of thermodynamic calculations of SiO_2 (C_c) initial concentration at initial concentration change of NH_4OH ($\blacksquare$) and experimentally obtained concentration (C_e) ($\bullet$)

In our opinion, the explanation for the difference in the results is the high concentration of NH_4OH (a weak base) in the solution at the completion of the reaction. And as a consequence, the pH value is 10.8 and above, which leads to a higher concentration of water-dissolved silicon ions compared to the theoretically calculated value. In thermodynamic calculations, the pH ranges from 6 to 7, which is explained by the partial conversion of NH_4OH into N_2 and NH_3 and their removal from the solution in the form of gas.

Conclusions Under conditions of thermodynamic equilibrium, obtaining the maximum solids SiO_2 at different initial concentrations $(C_2H_5O)_4Si$ is achieved at an initial concentration of C_2H_5OH of more than 1 mol/l. The solid phase concentration of SiO_2 is proportional to the initial concentration of TEOS.

Thermodynamic studies show that SiO_2 can be obtained at an initial concentration of H_2O equal to 0 M. The increase in the initial concentration of NH_4OH from 0 to 1.9 M leads to a decrease in the SiO_2 solid phase in the SI-O-H-C-N system for $1e^{-5} \text{ M}$, regardless of the initial concentration of

TEOS. The change in reaction temperature from 1 to 70 °C does not affect the concentration of ionic silicon compounds in the solution and solid SiO₂ phase.

Due to the kinetic constraints of the hydrolysis reaction of the TEOS, the practical yield of SiO₂ is less than the theoretical by 10...15 %, depending on the initial concentrations of reagents.

Further study of the problem of obtaining mono-dispersed particles SiO₂ should be directed to the experimental study of the SI-O-H-C-N system in order to detect the influence of technological parameters on the shape, average size and dispersion of the sizes of synthesized particles.

Література

1. Photonic crystal microspheres/ A.A. Zhokhov et al. *Optical Materials*. 2015. Vol. 49. P. 208–212.
2. Stöber silica particles as basis for redox modifications: particle shape, size, polydispersity, and porosity/ N. Plumere et al. *Journal of Colloid and Interface Science*. 2012. Vol. 368, № 1. PP. 208–219.
3. Фролов Ю.Г. Теоретические основы синтеза гидрозолей кремнезема. Получение и применение гидрозолей кремнезема. *Труды Моск. хим.-техн. ин-та им. Д.И. Менделеева*. 1979. № 107. С. 3–20.
4. Synthesis and optimization of colloidal silica nanoparticles and their functionalization with methacrylic acid/ T.M. Arantes et al. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2012. № 415. P. 209–217.
5. Tadanaga K., Morita K., Mori K., Tatsumisago, M. Synthesis of monodispersed silica nanoparticles with high concentration by the Stöber process. *Journal of Sol-Gel Science and Technology*. 2013. № 68 (2). P. 341–345.
6. Theoretical Study of the Thermochemistry of Molecules in the Si-O-H System/ Mark, D., et al. *J. Phys. Chem.* 1995. № 99. P. 15285–15293.
7. First-Principles Thermochemistry for Silicon Species in the Decomposition of Tetraethoxysilane/ Phadungsukanan W. et al. *J. Phys. Chem. A*. 2009. Vol.13, № 31. P 9041–9049.
8. Масалов В.М., Сухинина Н.С., Омельченко Г.А. Наноструктура частиц диоксида кремния, полученных многоступенчатым методом штобера-финка-бона. *Хімія, фізика та технологія поверхні*. 2011. Т. 2, № 4. С. 373–384.

References

1. Zhokhov A.A., Masalov V.M., & Sukhinina N.S. (2015). Photonic crystal microspheres. *Optical Materials*, 49, 208–212.
2. Plumere N., Ruff A., & Speiser B. (2012). Stöber silica particles as basis for redox modifications: particle shape, size, polydispersity, and porosity. *Journal of Colloid and Interface Science*, 368(1), 208–219.
3. Frolov Yu.G. (1979). Theoretical foundations for the synthesis of silica hydrosols. Preparation and use of silica hydrosols. *Proceedings of Moscow. chem.-tech. institute of D.I. Mendeleev*, 107, 3–20.
4. Arantes T.M., Pinto A.H., & Leite E.R. (2012). Synthesis and optimization of colloidal silica nanoparticles and their functionalization with methacrylic acid. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 415, 209–217.
5. Tadanaga K., Morita K., Mori K., & Tatsumisago M. (2013). Synthesis of monodispersed silica nanoparticles with high concentration by the Stöber process. *Journal of Sol-Gel Science and Technology*, 68(2), 341–345.
6. Mark D., Melius A.F., Melius C.F., Ho P., & Zachariah M.R. (1995). Theoretical Study of the Thermochemistry of Molecules in the Si-O-H System. *J. Phys. Chem.*, 99, 15285–15293.
7. Phadungsukanan W., Shekar S., & Shirley R. (2009). First-Principles Thermochemistry for Silicon Species in the Decomposition of Tetraethoxysilane. *J. Phys. Chem. A*, 13(31), 9041–9049.
8. Masalov V.M., Sukhinina N.S., & Omelchenko G.A. (2011). The nanostructure of silicon dioxide particles obtained by the multi-step Stober-Finca-Bon method. *Chemistry, physics and surface technology*, 2(4), 373–384.

Каюн Ігор Георгійович; Kayun Igor, ORCID: <http://orcid.org/0000-0001-7175-7551>

Мисов Олег Петрович; Mysov Oleg, ORCID: <http://orcid.org/0000-0003-2114-1382>

Received March 13, 2018

Accepted March 23, 2018